

5

## ADVANCED HIGH TEMPERATURE CORROSION RESISTANT ALLOY

### ABSTRACT

10

A nickel-base alloy consisting of, in weight percent, 42 to 58 nickel, 21 to 28 chromium, 12 to 18 cobalt, 4 to 9.5 molybdenum, 2 to 3.5 aluminum, 0.05 to 2 titanium, at least one microalloying agent selected from the group consisting of 0.005 to 0.1 yttrium and 0.01 to 0.6 zirconium, 0.01 to 0.15 carbon, 0 to 0.01 boron, 0 to 4 iron, 0 to 1

15

manganese, 0 to 1 silicon, 0 to 1 hafnium, 0 to 0.4 niobium, 0 to 0.1 nitrogen, incidental impurities and deoxidizers.

05183749-050490